

MINFILE Number:		Name:		Status:	
Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments	
3 2017	N	Assay/analysis Rock	Copper Zinc Silver	0.208 % 0.502 % 11.8 g/t	A rock chip sample (S-17-12) of the mineralized gossanous zone. Assessment Report 36824
FLOAT 2017	N	Assay/analysis Grab	Iron Copper Gold	24.36 % 4.24 % 0.63 g/t	A float boulder sample (S-17-30) from the Storey zone. Assessment Report 36824
SOUTHEAST 2017	N	Assay/analysis Rock	Copper Silver Iron	0.22 % 4.8 g/t 24.36 %	An outcrop sample from the fifth zone. Assessment Report 36824
STORIE 2017	N	Assay/analysis Chip	Iron	31.11 %	Five chip samples (S-17-24 through -28) yielded from 12.31 to 31.11 per cent iron from the Storey zone. Assessment Report 36824
SAMPLE 1989	N	Assay/analysis Grab	Copper Cadmium Zinc	0.259 % 0.101 % 14.9 %	In 1989, a sample (SZ-1) assayed 0.101 per cent cadmium, 0.259 per cent copper and 14.9 per cent zinc. Assessment Report 20092
SAMPLE 1988	N	Assay/analysis Grab	Copper Zinc	0.49 % 0.31 %	In 1988, a sample assayed 0.49 per cent copper and 0.31 per cent zinc over 0.6 metre. Assessment Report 18704