

<b>MINFILE Number:</b> 092L 133	<b>Name:</b> MARTHA 4	<b>Status:</b> Showing
---------------------------------	-----------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
3		Copper	0.208 %	A rock chip sample (S-17-12) of the mineralized gossanous zone. Assessment Report 36824
	Assay/analysis	Zinc	0.502 %	
2017	Rock	Silver	11.8 g/t	
FLOAT		Iron	24.36 %	A float boulder sample (S-17-30) from the Storey zone. Assessment Report 36824
	Assay/analysis	Copper	4.24 %	
2017	Grab	Gold	0.63 g/t	
SOUTHEAST		Copper	0.22 %	An outcrop sample from the fifth zone. Assessment Report 36824
	Assay/analysis	Silver	4.8 g/t	
2017	Rock	Iron	24.36 %	
STORIE		Iron	31.11 %	Five chip samples (S-17-24 through -28) yielded from 12.31 to 31.11 per cent iron from the Storey zone. Assessment Report 36824
2017	Assay/analysis Chip			
SAMPLE		Copper	0.259 %	In 1989, a sample (SZ-1) assayed 0.101 per cent cadmium, 0.259 per cent copper and 14.9 per cent zinc. Assessment Report 20092
	Assay/analysis	Cadmium	0.101 %	
1989	Grab	Zinc	14.9 %	
SAMPLE		Copper	0.49 %	In 1988, a sample assayed 0.49 per cent copper and 0.31 per cent zinc over 0.6 metre. Assessment Report 18704
	Assay/analysis	Zinc	0.31 %	
1988	Grab			