

<b>MINFILE Number:</b> 092L 134	<b>Name:</b> BOB 21	<b>Status:</b> Showing
---------------------------------	---------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SKARN		Copper	5.1 %	In 1994, chip samples yielded up to 5.1 per cent copper and 1.67 grams per tonne gold over 1.0 metre width. Assessment Report 23551
1994      N	Assay/analysis Chip	Gold	1.67 g/t	