

MINFILE Inventory Detail Report BC Geological Survey Ministry of Energy, Mines and Petroleum Resources

MINFILE Number: 092L 164			Name: BONANZA PIT		Status: Past Producer
Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
PIT		Assay/analysis Rock	Silver 4	10.05 % 49.3 g/t 0.084 g/t	Six rock samples (A1 through A6) from the Bonanza pit yielded from 0.55 to 10.05 per cent copper with up to
2018	N				greater than 50 per cent iron, 49.3 grams per tonne silver and 0.084 gram per tonne gold. Assessment Report 38244
PIT		Assay/analysis Chip	Copper Silver	7.73 % 80 g/t	A chip sample (GR-2) from the Bonanza pit over metres.
2013	N				Assessment Report 34322
DRILLHOL	LE	Assay/analysis	Silver Copper	2.8000 g/t 0.3800 %	The main copper zone over 16 metres in Zone E. Assessment Report 24601, page 1.
1994	N	Drill Core			
SAMPLE		Assay/analysis	Copper	3.8 %	In 1994, sampling yielded an average grade of 3.8 per cent copper over 5 metres; including 1.4 metres grading
1994	N	Rock			8.9 per cent copper and 0.242 grams per tonne gold. Assessment Report 23551