MINFILE Number: 092L 170 **Name:** ROONEY 1-4 **Status:** Showing

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 2018 N	Assay/analysis Rock	Copper	0.322 %	rock sample R2 Assessment Report 38134
VEIN 2011 N	Assay/analysis Rock	Copper Silver Gold	0.701 % 18.6 g/t 6.582 g/t	five rock samples (6749, 6985, 6986, 6991 and 16543) of actinolite and pyrite vein material yielded from 1.577 to 6.582 grams per tonne gold, 3.0 to 18.6 grams per tonne silver and 0.085 to 0.701 per cent copper Assessment Report 32553
SAMPLE 2004 N	Assay/analysis Grab	Silver Copper	6 g/t 1.24 %	a sample (C359) assayed 1.24 per cent copper and 6.0 grams per tonne silver, while another sample (C401) of massive basalt with malachite and rusty joints, located approximately 250 metres to the northwest, yielded 0.106 per cent copper Assessment Report 27463
2 2002 N	Assay/analysis Rock	Copper Silver	1.26 % 6.0 g/t	a sample from the Oreo zone Assessment Report 27070
SAMPLE 1969 N	Assay/analysis Chip	Copper	0.23 %	a chip sample assayed 0.14 per cent copper over 6.0 metres, while approximately 250 metres to the northwest another chip sample yielded 0.23 per cent copper over 6.0 metres Assessment Report 1859, Figure 2.