

<b>MINFILE Number:</b>	092L 170	<b>Name:</b>	ROONEY 1-4	<b>Status:</b>	Showing
------------------------	----------	--------------	------------	----------------	---------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE		Copper	0.322 %	rock sample R2
2018	N	Assay/analysis Rock		Assessment Report 38134
VEIN		Copper	0.701 %	five rock samples (6749, 6985, 6986, 6991 and 16543) of actinolite and pyrite vein material yielded from 1.577
2011	N	Assay/analysis Rock	Silver Gold	to 6.582 grams per tonne gold, 3.0 to 18.6 grams per tonne silver and 0.085 to 0.701 per cent copper Assessment Report 32553
SAMPLE		Silver	6 g/t	a sample (C359) assayed 1.24 per cent copper and 6.0
2004	N	Assay/analysis Grab	Copper	grams per tonne silver, while another sample (C401) of massive basalt with malachite and rusty joints, located approximately 250 metres to the northwest, yielded 0.106 per cent copper Assessment Report 27463
2		Copper	1.26 %	a sample from the Oreo zone
2002	N	Assay/analysis Rock	Silver	Assessment Report 27070
SAMPLE		Copper	0.23 %	a chip sample assayed 0.14 per cent copper over 6.0 metres, while approximately 250 metres to the northwest another chip sample yielded 0.23 per cent copper over 6.0 metres
1969	N	Assay/analysis Chip		Assessment Report 1859, Figure 2.