

| MINFILE Number:             |   | 092L 178             | Name:     |           | NUGGET QUEEN   | Status: | Past Producer |  |  |
|-----------------------------|---|----------------------|-----------|-----------|--|---------|---------------|--|--|
| Ore Zone/<br>Year/Report On |   | Tonnage/<br>Category | Commodity | Grade     | Reference/<br>Comments                                   |         |               |  |  |
| 2                           |   |                      | Gold      | 1.63 g/t  | sample 01527   |         |               |  |  |
|                             |   | Assay/analysis       |           |           | Assessment Report 27565                                  |         |               |  |  |
| 2004                        | N | Chip                 |           |           |  |         |               |  |  |
| 3                           |   |                      | Gold      | 5.52 g/t  | a 0.9 metre discontinuous channel sample (01530)         |         |               |  |  |
|                             |   | Assay/analysis       |           |           | Assessment Report 27565                                  |         |               |  |  |
| 2004                        | N | Channel              |           |           |  |         |               |  |  |
| VEIN                        |   |                      | Gold      | 6.1 g/t   | grab sample (20764) of vein 8                            |         |               |  |  |
|                             |   | Assay/analysis       | Silver    | 81.2 g/t  | Assessment Report 26391                                  |         |               |  |  |
| 2000                        | N | Grab                 | Copper    | 0.142 %   |  |         |               |  |  |
|                             |   |                      | Lead      | 1.16 %    |  |         |               |  |  |
|                             |   |                      | Zinc      | 0.093 %   |  |         |               |  |  |
| VEINS                       |   |                      | Gold      | 8.8 g/t   | grab sample (20758) of silicified metasediments adjacent |         |               |  |  |
|                             |   | Assay/analysis       |           |           | to the vein 8  |         |               |  |  |
| 2000                        | N | Grab                 |           |           | Assessment Report 26391                                  |         |               |  |  |
| 2                           |   |                      | Gold      | 4.3 g/t   |  |         |               |  |  |
|                             |   | Assay/analysis       |           |           | Assessment Report 24958                                  |         |               |  |  |
| 1996                        | N | Rock                 |           |           |  |         |               |  |  |
| VEIN                        |   |                      | Gold      | 22.31 g/t | seventeen samples of the 4 vein yielded and uncut        |         |               |  |  |
|                             |   | Assay/analysis       | Silver    | 30.4 g/t  | average grade of 22.31 grams per tonne gold, 30.4 grams  |         |               |  |  |
| 1996                        | N | Rock                 | Lead      | 0.337 %   | per tonne silver and 0.337 per cent lead over an average |         |               |  |  |
|                             |   |                      |           |           | width of 0.49 metres                                     |         |               |  |  |
|                             |   |                      |           |           | Assessment Report 24958                                  |         |               |  |  |
| VEINS                       |   |                      | Gold      | 13.0 g/t  | six samples of vein 5 material yielded values from 0.005 |         |               |  |  |
|                             |   | Assay/analysis       |           |           | to 13.0 grams per tonne gold                             |         |               |  |  |
| 1995                        | N | Rock                 |           |           | Assessment Report 24958                                  |         |               |  |  |
| VEIN                        |   |                      | Gold      | 69.95 g/t | assay plan of the 4 vein, sampled on 1.5 metre centres   |         |               |  |  |
|                             |   | Assay/analysis       |           |           | over a strike length of 65 metres returned a maximum     |         |               |  |  |
| 1938                        | N | Unknown              |           |           | value of 69.95 grams per tonne gold over 0.9 metre       |         |               |  |  |
|                             |   |                      |           |           | (sample Number 1597)                                     |         |               |  |  |
|                             |   |                      |           |           | Property File: Bobmac Mine, Drawing 4                    |         |               |  |  |
| 3                           |   |                      | Gold      | 63 g/t    |  |         |               |  |  |
|                             |   | Assay/analysis       | Silver    | 19 g/t    |  |         |               |  |  |
| 1938                        | N | Rock                 |           |           | In 1938, eight vein samples yielded an average of 63     |         |               |  |  |
|                             |   |                      |           |           | grams per tonne gold, 19 grams per tonne silver over an  |         |               |  |  |
|                             |   |                      |           |           | average width of 0.31 metres                             |         |               |  |  |
|                             |   |                      |           |           | Assessment Report 24958                                  |         |               |  |  |