

|                        |          |              |                     |                |                    |
|------------------------|----------|--------------|---------------------|----------------|--------------------|
| <b>MINFILE Number:</b> | 092L 208 | <b>Name:</b> | SMITH COPPER (MAIN) | <b>Status:</b> | Developed Prospect |
|------------------------|----------|--------------|---------------------|----------------|--------------------|

| Ore Zone/<br>Year/Report On |   | Tonnage/<br>Category         | Commodity | Grade       | Reference/<br>Comments  |
|-----------------------------|---|------------------------------|-----------|-------------|---|
| 1988                        | N | Assay/analysis<br>Drill Core | Copper    | 1.22 %      | In 1988, drilling intersected 1.1 metres assaying 1.2 per cent copper and 17.0 per cent zinc in hole N88-03 on the western edge of the occurrence.<br>Assessment Report 18704   |
|                             |   |                              | Zinc      | 17 %        |   |
| 1981                        | Y | Indicated                    | Silver    | 64.4000 g/t | Drill indicated.<br>George Cross News Letter December 7, 1988.  |
|                             |   |                              | Copper    | 1.6900 %    |   |
|                             |   |                              | Lead      | 3.7000 %    |   |
|                             |   |                              | Zinc      | 12.5000 %   |   |
| 1981                        | N | Assay/analysis<br>Drill Core | Copper    | 0.67 %      | In 1981, diamond drilling intersected mineralized sections yielding up to 0.67 per cent copper, 0.25 per cent lead, 10.87 per cent zinc and 17.1 grams per tonne silver over 4.5 metres in DDH J-3-81. Another drill hole (DDH J-9-81) intersected 0.17 per cent copper, 5.08 per cent lead, 8.88 per cent zinc and 106.3 grams per tonne silver over 0.8 metre.<br>Assessment Report 10337 |
|                             |   |                              | Lead      | 0.25 %      |   |
|                             |   |                              | Zinc      | 10.87 %     |   |
|                             |   |                              | Silver    | 17.1 g/t    |   |
| 1981                        | N | Assay/analysis<br>Chip       | Copper    | 1.18 %      | Chip sampling (CI-62642), performed during same year, yielded up to 1.18 per cent copper, 19.4 per cent lead, 11.5 per cent zinc and 101.5 grams per tonne silver over 0.6 metre.<br>Assessment Report 10337  |
|                             |   |                              | Lead      | 19.4 %      |   |
|                             |   |                              | Zinc      | 11.5 %      |   |
|                             |   |                              | Silver    | 101.5 g/t   |   |