

MINFILE Number:	092L 229	Name:	DAVIS	Status:	Showing
------------------------	----------	--------------	-------	----------------	---------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
FLOAT			Silver	254.8 g/t	In 1996, two float samples of massive sphalerite taken from a ridge, approximately 1 kilometres to the south west, yielded greater than 1 per cent zinc and up to 254.8 grams per tonne silver Assessment Report 24946
1996	N	Assay/analysis Rock			
DRILLHOLE			Copper	1.86 %	In 1990, drill hole 90-5 located a faulted extension of the main vein to the south, at a depth of 64.9 to 65.6 metres, yielding 1.86 per cent copper over 0.7 metres Assessment Report 20075
1990	N	Assay/analysis Drill Core			
DRILLHOLE			Copper	6.5 %	In 1989, drill hole 89-5 intersected the mineralized quartz vein yielding:
1989	N	Assay/analysis	Silver	50.1 g/t	
		Drill Core	Gold	0.14 g/t	
		Sample No. Intercept Copper Silver			
		Gold			
		(metres) (per cent) (g/t)			
		(g/t)			
		61345	0.4 to 1.8	>1.0	21.4
		N/A			
		61346	1.8 to 3.0	6.5	50.1
		0.21			
61347	3.0 to 4.2	4.1	32.9		
0.14					
(Assessment Report 19452).					
Assessment Report 19452					
SAMPLE			Arsenic	3.6000 %	Sample of second type of mineralization.
1985	N	Assay/analysis	Gold	1.3000 g/t	
		Channel			Assessment Report 13836.
VEIN			Silver	20.0000 g/t	Sample over 0.5 metres.
1985	N	Assay/analysis	Copper	2.4200 %	
		Chip			Assessment Report 13836, page 13.