

| | | | | | |
|------------------------|----------|--------------|------------------|----------------|---------|
| MINFILE Number: | 092L 236 | Name: | TUSCARORA (L.84) | Status: | Showing |
|------------------------|----------|--------------|------------------|----------------|---------|

| Ore Zone/ Year/Report On | | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|-----------------------------|---|------------------------|-----------|----------|--|
| SAMPLE 1999 | N | Assay/analysis Grab | Zinc | 10 % | Select grab samples yielded greater than 10 per cent zinc with copper values from 0.1 to 0.3 per cent and up to 7.3 grams per tonne silver. Assessment Report 26040 |
| | | | Copper | 0.3 % | |
| | | | Silver | 7.3 g/t | |
| SAMPLE 1998 | N | Assay/analysis Grab | Copper | 0.26 % | Grab sample from a 1.0 metre wide fracture zone; other samples yielded up to 6.4 per cent zinc. Assessment Report 25797 |
| | | | Zinc | 3.77 % | |
| | | | Silver | 5.6 g/t | |
| SAMPLE 1971 | N | Assay/analysis Chip | Zinc | 2.0000 % | Copper also present. Assessment Report 3165, page 11. |
| | | | | | |