

<b>MINFILE Number:</b> 092L 255	<b>Name:</b> WHITE FANG	<b>Status:</b> Prospect
---------------------------------	-------------------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
OUTCROP		Copper	13.49 %	Six rock samples (J-7 through J-12) taken from the occurrence area yielded from 0.04 to 13.49 per cent copper with 24.09 to 73.71 per cent iron. Assessment Report 37313
2017 N	Assay/analysis Rock			
SAMPLE		Copper	0.29 %	Assessment Report 23551
1994 N	Assay/analysis Chip			
DRILLHOLE		Copper Silver	0.38 % 2.8 g/t	Assessment Report 24601
1994 N	Assay/analysis Drill Core			
SKARN		Copper	3.0000 %	Maximum value from finely disseminated chalcopyrite within massive garnet. McDougall, J.J., 1961: Report on Bonanza Lake copper.
1961 N	Assay/analysis Grab			
SAMPLE		Magnetite	80.0000 %	Magnetite body, 3 to 63 metres wide, 100 metres northeast of the White Fang showing. Property File - McDougall, J.J., 1961.
1961 N	Assay/analysis Grab			