MINFILE Number: 092L 255 **Name:** WHITE FANG **Status:** Prospect

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
OUTCROP 2017	N	Assay/analysis Rock	Copper	13.49 %	Six rock samples (J-7 through J-12) taken from the occurrence area yielded from 0.04 to 13.49 per cent copper with 24.09 to 73.71 per cent iron. Assessment Report 37313
SAMPLE 1994	N	Assay/analysis Chip	Copper	0.29 %	Assessment Report 23551
DRILLHOLE 1994	N	Assay/analysis Drill Core	Copper Silver	0.38 % 2.8 g/t	Assessment Report 24601
SKARN 1961	N	Assay/analysis Grab	Copper	3.0000 %	Maximum value from finely disseminated chalcopyrite within massive garnet. McDougall, J.J., 1961: Report on Bonanza Lake copper.
SAMPLE 1961	N	Assay/analysis Grab	Magnetite	80.0000 %	Magnetite body, 3 to 63 metres wide, 100 metres northeast of the White Fang showing. Property File - McDougall, J.J., 1961.