

| | | |
|---------------------------------|--------------------------|-----------------------------------|
| MINFILE Number: 092L 301 | Name: HILLER 8-12 | Status: Developed Prospect |
|---------------------------------|--------------------------|-----------------------------------|

| Ore Zone/ Year/Report On | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|-----------------------------|------------------------------|---------------------------|----------------------------|---|
| HILLER 8 1988 N | 272 kt Indicated | Iron | 35 % | Property File - Footwall Explorations Ltd. [1988-05-24]: Prospectus Report on the Hiller-Churchill Group |
| HILLER 8 1967 Y | 180 kt Indicated | Iron | 30.0000 % | Iron grades 30 to 40 per cent. Drill indicated reserves contained in two pods. Property File - Saukko, 1967. |
| DRILLHOLE 1965 N | Assay/analysis Drill Core | Iron | 50.76 % | Iron over 12.6 metres in hole H-14. Property File - R.N. Saukko [1966-02-10]: Report on Hiller-Churchill Deposit 1965 |
| DRILLHOLE 1965 N | Assay/analysis Drill Core | Iron | 60.09 % | Over 11.7 metres in hole H-16. Property File - R.N. Saukko [1966-02-10]: Report on Hiller-Churchill Deposit 1965 |
| DRILLHOLE 1964 N | Assay/analysis Drill Core | Iron Sulphur Copper | 42.0 % 1.58 % 0.04 % | The average of 87 samples from 251.7 metres of drill. Property File - J.J. McDougall [1965-01-12]: Report on Hiller Magnetite Properties 1964 |