

MINFILE Number: 092L 356	Name: CRULLER	Status: Showing
---------------------------------	----------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
E 2018 N	Assay/analysis Chip	Copper Silver	5.27 % 24.0 g/t	A 1.0 metre chip sample (R7) of the shear zone from the Éclair zone, while a sample (R6) from a 10-centimetre-wide seam of massive sulphide in a shear zone assayed 14.95 per cent copper and 27.4 grams per tonne silver. MacIntyre, D. (2018-07-18): Technical Report - Red Metal Ridge Mineral Property
E 2011 N	Assay/analysis Grab	Copper	6.09 %	In 2011, sampling of the Eclair zone yielded up to 6.09 per cent copper. Assessment Report 32553
C 2010 N	Assay/analysis Grab	Copper Silver	2.83 % 6 g/t	In 2010, sampling of the Cruller zone returned up to 2.83 per cent copper and 6 grams per tonne silver. Assessment Report 31856
C 2006 N	Assay/analysis Grab	Copper Silver Gold	2.71 % 5.6 g/t 0.35 g/t	In 2006, sampling of Cruller occurrence yielded up to 2.71 per cent copper, 5.6 grams per tonne silver and 0.35 grams per tonne gold. Assessment Report 28747).