

<b>MINFILE Number:</b> 092L 359	<b>Name:</b> KRINGLE	<b>Status:</b> Showing
---------------------------------	----------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 2006	N Assay/analysis Grab	Molybdenum Vanadium	0.018 % 0.218 %	In 2006, a sample (A8-79) assayed 0.018 per cent molybdenum and 0.218 per cent vanadium. Assessment Report 31039
SAMPLE 2006	N Assay/analysis Grab	Copper	1.14 %	A sample (L505.50) of granite with pyrite and chalcopyrite. Assessment Report 31039
SAMPLE 2002	N Assay/analysis Grab	Copper Silver Molybdenum Iron	7.05 % 67.2 g/t 0.112 % 36.7 %	In 2002, a sample (E187880) of malachite-stained, argillically altered felsite(?) returned 7.05 per cent copper, 67.2 grams per tonne silver. Another sample (E187881) returned 0.112 per cent molybdenum with 0.203 per cent copper. Samples of massive magnetite yielded up to 36.7 per cent iron. Assessment Report 26930