

<b>MINFILE Number:</b>	092L 359	<b>Name:</b>	KRINGLE	<b>Status:</b>	Showing
------------------------	----------	--------------	---------	----------------	---------

<b>Ore Zone/ Year/Report On</b>		<b>Tonnage/ Category</b>	<b>Commodity</b>	<b>Grade</b>	<b>Reference/ Comments</b>
SAMPLE  2006	N	Assay/analysis Grab	Molybdenum	0.018 %	In 2006, a sample (A8-79) assayed 0.018 per cent molybdenum and 0.218 per cent vanadium. Assessment Report 31039
			Vanadium	0.218 %	
SAMPLE  2006	N	Assay/analysis Grab	Copper	1.14 %	A sample (L505.50) of granite with pyrite and chalcopyrite. Assessment Report 31039
SAMPLE  2002	N	Assay/analysis Grab	Copper	7.05 %	In 2002, a sample (E187880) of malachite-stained, argillically altered felsite(?) returned 7.05 per cent copper, 67.2 grams per tonne silver. Another sample (E187881) returned 0.112 per cent molybdenum with 0.203 per cent copper. Samples of massive magnetite yielded up to 36.7 per cent iron. Assessment Report 26930
			Silver	67.2 g/t	
			Molybdenum	0.112 %	
			Iron	36.7 %	