

MINFILE Number:		092N 075	Name: DXG		Status: Showing	
Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments	
SAMPLE	Ν	Assay/analysis Grab	Zinc Lead Silver	1 % 0.54 % 40 g/t	Analysis of Sample DXG-82. The analytical method used for sample DXG-82 and DXG-88 is limited to a maximum of 1 per cent for zinc and copper. Sample DXG-82 is located about 120 metres east of sample DXG-88. Assessment Report 9710.	
SAMPLE 1981	N	Assay/analysis Grab	Copper Gold Silver	1 % 0.25 g/t 40 g/t	Analysis of Sample DXG-88. Analytical method used on sample DXG-82 and DXG-88 was limited to a maximum of 1 per cent for zinc and copper. The analytical method used for sample DXG-82 and DXG-88 is limited to a maximum of 1 per cent for zinc and copper. Assessment Report 9710.	