

<b>MINFILE Number:</b> 092O 039	<b>Name:</b> BUR	<b>Status:</b> Prospect
---------------------------------	------------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
DRILLHOLE 1991 N	Assay/analysis Drill Core	Copper	0.14 %	Over 80.1 metres in hole 91-38. Westphal, M.W. (2011-03-10): Technical Report – Taseko Mineral Property
DRILLHOLE 1991 N	Assay/analysis Drill Core	Copper Gold	0.61 % 0.82 g/t	0.61 and 0.72 per cent copper with 0.82 and 0.58 gram per tonne gold over 14.1 and 13.2 metres, respectively, in hole 91-39. Westphal, M.W. (2011-03-10): Technical Report – Taseko Mineral Property
DRILLHOLE 1991 N	Assay/analysis Drill Core	Copper	0.13 %	Over 43.5 metres in hole 91-40. Westphal, M.W. (2011-03-10): Technical Report – Taseko Mineral Property
DRILLHOLE 1991 N	Assay/analysis Drill Core	Copper Gold	0.32 % 0.28 g/t	0.32 and 0.56 per cent copper with 0.28 and 0.17 gram per tonne gold over 59.7 and 19.8 metres in hole 91-54 Westphal, M.W. (2011-03-10): Technical Report – Taseko Mineral Property
DRILLHOLE 1991 N	Assay/analysis Drill Core	Copper Gold	0.26 % 0.08 g/t	Over 29.1 metres in hole 91-55. Westphal, M.W. (2011-03-10): Technical Report – Taseko Mineral Property
DRILLHOLE 1989 N	Assay/analysis Drill Core	Copper	0.27 %	Drill hole (89-13) located southwest of the Breccia zone, over 0.9 metre. Westphal, M.W. (2011-03-10): Technical Report – Taseko Mineral Property
DRILLHOLE 1976 N	Assay/analysis Drill Core	Copper	0.32 %	Drilling on the Breccia zone over 6.0 metres in hole Q-33. Westphal, M.W. (2011-03-10): Technical Report – Taseko Mineral Property
DRILLHOLE 1970 N	Assay/analysis Drill Core	Copper	0.20 %	Drill hole (S-1), located on the Breccia zone, over 30 metres, including 0.45 per cent copper over 6 metres. Westphal, M.W. (2011-03-10): Technical Report – Taseko Mineral Property
DRILLHOLE 1969 N	Assay/analysis Drill Core	Silver	153.2 g/t	Drill hole (A-6), located immediately northeast of the Taseko River, over 3.0 metres. Westphal, M.W. (2011-03-10): Technical Report – Taseko Mineral Property