

MINFILE Inventory Detail Report BC Geological Survey Ministry of Energy, Mines and Petroleum Resources

MINFILE Number: 092P 119 Name: GOLDEN LOON LOW GRADE ZONE Status: Prospect

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
997	N	Assay/analysis Grab	Gold Silver	8.3 g/t 66.7 g/t	A second area of mineralization, located approximately 100 metres along strike to the southeast of the trenched and drilled area, consists a north-trending vein up to 70 centimetres in width. Samples of the vein have yielded up to 8.3 grams per tonne gold and 66.7 grams per tonne silver, while the bleached and silicified wall rocks yielded values of up to 2.0 grams per tonne gold Assessment Report 25431
990	N	Assay/analysis Chip	Gold	4.5 g/t	Another silicified alteration zone is reported to be exposed approximately 70 metres south west of the second mineralized zone. The zones vary from 1 to 2 metres wide and dips steeply. Minor disseminated chalcopyrite occurs in the propylitic alteration haloes, while pyrite occurs along fractures. Samples of the zone have yielded up to 4.5 grams per tonne gold over 1 to 2 metres Property File - W. Kovacevic [1996-01-01]: Fact Sheet - Golden Loon
MAIN 1990	N	Assay/analysis Grab	Gold	1.17 g/t	sampling of trenches is reported to have yielded gold values in the 0.5 to 2.5 grams per tonne range occurring throughout the trench and average 1.17 grams per tonne for all samples Assessment Report 25434
1AIN 990	N	Assay/analysis Drill Core	Gold	2.67 g/t	Diamond drilling, performed below the trench(s), yielded 2.67 grams per tonne gold over 10.4 metres and 1.16 grams per tonne gold over 14.3 metres Property File - W. Kovacevic [1996-01-01]: Fact Sheet - Golden Loon

Friday, December 12, 2025 MINFILE Number: 092P 119 Page 1 of 1