

MINFILE Number:	092P 119	Name:	GOLDEN LOON LOW GRADE ZONE	Status:	Prospect
------------------------	----------	--------------	----------------------------	----------------	----------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
2			Gold	8.3 g/t	A second area of mineralization, located approximately 100 metres along strike to the southeast of the trenched and drilled area, consists a north-trending vein up to 70 centimetres in width. Samples of the vein have yielded up to 8.3 grams per tonne gold and 66.7 grams per tonne silver, while the bleached and silicified wall rocks yielded values of up to 2.0 grams per tonne gold
1997	N	Assay/analysis Grab	Silver	66.7 g/t	
3			Gold	4.5 g/t	Another silicified alteration zone is reported to be exposed approximately 70 metres south west of the second mineralized zone. The zones vary from 1 to 2 metres wide and dips steeply. Minor disseminated chalcopryite occurs in the propylitic alteration haloes, while pyrite occurs along fractures. Samples of the zone have yielded up to 4.5 grams per tonne gold over 1 to 2 metres Property File - W. Kovacevic [1996-01-01]: Fact Sheet - Golden Loon
1990	N	Assay/analysis Chip			
MAIN			Gold	1.17 g/t	sampling of trenches is reported to have yielded gold values in the 0.5 to 2.5 grams per tonne range occurring throughout the trench and average 1.17 grams per tonne for all samples Assessment Report 25434
1990	N	Assay/analysis Grab			
MAIN			Gold	2.67 g/t	Diamond drilling, performed below the trench(s), yielded 2.67 grams per tonne gold over 10.4 metres and 1.16 grams per tonne gold over 14.3 metres Property File - W. Kovacevic [1996-01-01]: Fact Sheet - Golden Loon
1990	N	Assay/analysis Drill Core			