

<b>MINFILE Number:</b> 092P 122	<b>Name:</b> TIM #1	<b>Status:</b> Prospect
---------------------------------	---------------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
1 2001 N	Assay/analysis Grab	Gold Copper	1.10 g/t 0.177 %	A sample of propylitic to potassic altered volcanic breccia containing pyrite, chalcopyrite mineralized sub-crop, located approximately 300 metres southwest of the Tim 1 zone. Church, C. (2008-06-20): Summary Report on the Tam and Mat Mineral Claims
2 2001 N	Assay/analysis Grab	Copper Gold Silver	1.915 % 0.22 g/t 64.5 g/t	Grab samples from the Tim 2 shear zone yielded from 0.212 to 1.915 per cent copper, 0.007 to 0.222 gram per tonne gold and 5.9 to 64.5 grams per tonne silver over 1 to 2 metre widths along a strike distance of 44 metres. Church, C. (2008-06-20): Summary Report on the Tam and Mat Mineral Claims
COPPER 2001 N	Assay/analysis Grab	Gold Copper	0.17 g/t 0.132 %	Sample from the 'Native Copper' zone. Church, C. (2008-06-20): Summary Report on the Tam and Mat Mineral Claims
DRILLHOLE 2001 N	Assay/analysis Drill Core	Copper Gold Silver	0.61 % 0.18 g/t 6.3 g/t	Over 17.4 metres in drillhole TAM01-1. EMPR ASS RPT 26655
SAMPLE 2001 N	Assay/analysis Grab	Copper Gold	0.1773 % 1.1 g/t	Sample TAM01DR-02. EMPR ASS RPT 26655
DRILLHOLE 1990 N	Assay/analysis Drill Core	Copper	0.76 %	Diamond drilling close to the volcanic-syenodiorite dike contact on the Tim1 zone yielded intercepts including 16.6 metres averaging 0.76 per cent copper and 15.0 metres averaging 0.40 per cent copper in holes P90-1 and P90-6, respectively. Church, C. (2008-06-20): Summary Report on the Tam and Mat Mineral Claims (Tam Property)
DRILLHOLE 1990 N	Assay/analysis Drill Core	Copper	0.69 %	Drill hole D90-10, drilled to test the possible northwest extension of the zone, cut the syenodiorite dike at a low angle yielding 0.69 per cent copper over 11.3 metres and 0.24 per cent copper over 51.8 metres. Church, C. (2008-06-20): Summary Report on the Tam and Mat Mineral Claims (Tam Property)
SAMPLE 1983 N	Assay/analysis Drill Core	Gold Copper	0.6000 g/t 2.7600 %	Sample width 42.7 metres. Assessment Report 12192.

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
2  1979	N  Assay/analysis Chip	Copper Gold	4.17 % 0.7 g/t	Over 1.07 metres from the southern trench. Church, C. (2008-06-20): Summary Report on the Tam and Mat Mineral Claims (Tam Property)