

<b>MINFILE Number:</b> 092P 160	<b>Name:</b> SC 3	<b>Status:</b> Prospect
---------------------------------	-------------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 2014	N Assay/analysis Rock	Gold	5.9 g/t	Sample 13CCTK059 Assessment Report 34982
SAMPLE 2013	N Assay/analysis Grab	Gold	1.119 g/t	grab sample 13CCMK-33 Assessment Report 34307
SAMPLE 1994	N Assay/analysis Rock	Gold	0.71 g/t	Sample 94KB-33 Assessment Report 23816
DRILLHOLE 1987	N Assay/analysis Drill Core	Gold	7.51 g/t	over 0.4 metres and 1.79 grams per tonne gold over 1.5 metres in hole Bar-10 Assessment Report 16996
DRILLHOLE 1987	N Assay/analysis Drill Core	Gold	0.71 g/t	over 16.5 metres, including 3.35 grams per tonne gold over 1.50 metres in hole Bar-9 Assessment Report 16996
DRILLHOLE 1987	N Assay/analysis Drill Core	Gold	0.59 g/t	over 9.0 metres in hole Bar-12 Assessment Report 16996
DRILLHOLE 1987	N Assay/analysis Drill Core	Silver Gold	109.7 g/t 1.25 g/t	over 0.45 metre, while another section yielded 1.25 grams per tonne gold over 1.5 metres in hole Bar-11 Assessment Report 16996
DRILLHOLE 1986	N Assay/analysis Drill Core	Silver Gold	134.0000 g/t 18.0000 g/t	A sample of 30 centimetres of massive pyrite, from a 2.52 metre section yielding 4.45 grams per tonne gold. A separate, lower, section of the drill hole yielded 0.242 grams per tonne gold over 13.98 metres. Assessment Report 15856. Assessment Report 15856