

MINFILE Number: 093A 043	Name: SPANISH MOUNTAIN	Status: Developed Prospect
---------------------------------	-------------------------------	-----------------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
DRILLHOLE 2026 N	Assay/analysis Drill Core	Gold	0.70 g/t	26-DH-1337: 282.5 metre intercept from 91.5 metres downhole, including 116.8 metres of 1.20 grams per tonne gold PR REL Spanish Mountain Gold Ltd. Mar. 10, 2026
DRILLHOLE 2024 N	Assay/analysis Drill Core	Gold	2.55 g/t	DDH 1268: 29 metre intercept, including 6 metres grading 3.36 grams per tonne gold and 9 metres grading 3.19 grams per tonne gold PR REL Spanish Mountain Gold Ltd Dec. 18, 2024
MAIN 2021 Y	294,153 kt Combined	Gold Silver	0.50 g/t 0.72 g/t	Measured and indicated using a 0.15 gram per tonne gold cut-off grade. Moose Mountain Technical Services (2021-05-31): Spanish Mountain Gold Project Prefeasibility Study NI 43-101 Technical Report
MAIN 2021 Y	95,900 kt Combined	Gold Silver	0.76 g/t 0.71 g/t	Proven and probable reserve using a 0.30 gram per tonne gold cut-off grade. Moose Mountain Technical Services (2021-05-31): Spanish Mountain Gold Project Prefeasibility Study NI 43-101 Technical Report
MAIN 2021 Y	18,343 kt Inferred	Gold Silver	0.63 g/t 0.76 g/t	Silver using a 0.15 gram per tonne gold cut-off grade. Moose Mountain Technical Services (2021-05-31): Spanish Mountain Gold Project Prefeasibility Study NI 43-101 Technical Report
MAIN 2016 Y	181,352 kt Inferred	Gold Silver	0.31 g/t 0.65 g/t	Using a 0.15 gram per tonne gold cut-off. Schulte, M. (2019-02-11): NI 43-101 Preliminary Economic Assessment for the Spanish Mountain Gold Property
MAIN 2016 Y	270,140 kt Combined	Gold Silver	0.40 g/t 0.67 g/t	Measured and indicated, using a 0.15 gram per tonne gold cut-off. Schulte, M. (2019-02-11): NI 43-101 Preliminary Economic Assessment for the Spanish Mountain Gold Property
MAIN 2014 Y	310,970 kt Inferred	Gold Silver	0.35 g/t 0.63 g/t	Using a cut-off grade of 0.20 gram per tonne gold. Giroux, G.H., Koffyberg, A. (2014-04-25): Technical Report on an Updated Mineral Resource Estimate on the Spanish Mountain Gold Deposit
MAIN 2014 Y	237,830 kt Combined	Gold Silver	0.46 g/t 0.69 g/t	Using a cut-off grade of 0.20 gram per tonne gold. Giroux, G.H., Koffyberg, A. (2014-04-25): Technical Report on an Updated Mineral Resource Estimate on the Spanish Mountain Gold Deposit

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
MAIN 2009 Y	102,260 kt Combined	Gold	0.785 g/t	Based on a 0.50 grams per tonne gold cut-off. News Release Stockwatch March 18, 2009
MAIN 2009 Y	11,650 kt Inferred	Gold	0.787 g/t	Based on a 0.50 grams per tonne gold cut-off. News Release Stockwatch March 18, 2009.