

MINFILE Number: 093A 079	Name: BREN	Status: Prospect
---------------------------------	-------------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
TRENCH 2012 N	Assay/analysis Rock	Gold	0.37 g/t	sampling of trenches from the silica cap zone Assessment Report 33259
TRENCH 2012 N	Assay/analysis Rock	Copper Molybdenum Silver Gold	0.311 % 0.014 % 22 g/t 0.83 g/t	trenching on an 80 metre long oxidized saprolitic gossan zone, in excess of 8 metres depth and located along a granodiorite-silica cap contact Assessment Report 33259
TRENCH 2012 N	Assay/analysis Rock	Gold Silver Zinc	16.6 g/t 16 g/t 0.163 %	sample (K190655) from the former "Bren" (Glory Hole) trenches of gold bearing arsenopyrite mineralization Assessment Report 33259
DRILLHOLE 2008 N	Assay/analysis Drill Core	Molybdenum Rhenium	0.200 % 0.0943 %	re-sampling of two quartz-molybdenite mineralized sections of drill core from hole K-3 Assessment Report 30356
DRILLHOLE 2000 N	Assay/analysis Drill Core	Molybdenum	0.021 %	over 59 metres in hole K-2 Assessment Report 26317
DRILLHOLE 2000 N	Assay/analysis Drill Core	Molybdenum	0.032 %	over 87 metres in hole K-3 Assessment Report 26317
TRENCH 1996 N	Assay/analysis Grab	Gold Silver Zinc	32.8 g/t 55.4 g/t 4.6 %	grab sample (BF-96-07) of mineralized vein material from a past trench Assessment Report 24717
TRENCH 1996 N	Assay/analysis Chip	Gold	1.06 g/t	a 5.0 metre chip sample (BF-96-06) from the trenched area Assessment Report 24717
TRENCH 1996 N	Assay/analysis Chip	Gold	0.11 g/t	chip sampling of new trenches (TR96-01), west of the past trenches, over 20 metres Assessment Report 24717
ROADCUT 1995 N	Assay/analysis Rock	Molybdenum Copper Tungsten Gold	1 % 0.30 % 0.08 % 0.44 g/t	a sample of mineralized ferricrete, exposed by a new road cut Assessment Report 25734

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
TRENCH 1983 N	Assay/analysis Rock	Silver Gold Zinc	14.9 g/t 10.0 g/t 1.00 %	rock samples of narrow mineralized veins exposed by an area of trenching yielded up to 14.9 grams per tonne silver and greater than 10.0 grams per tonne gold and 1.00 per cent zinc Assessment Report 12363