

| | | | | | |
|------------------------|----------|--------------|-------|----------------|---------|
| MINFILE Number: | 093A 154 | Name: | TRUMP | Status: | Showing |
|------------------------|----------|--------------|-------|----------------|---------|

| Ore Zone/ Year/Report On | | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|-----------------------------|---|------------------------|-----------|-----------|--|
| SAMPLE | | Assay/analysis Grab | Silver | 2310 g/t | sample of pure galena (LC-04) |
| | | | Lead | 76.8 % | Assessment Report 32209 |
| 2010 | N | | | | |
| VEIN | | Assay/analysis Rock | Silver | 1850 g/t | sample LC-03 |
| | | | Lead | 56.5 % | Assessment Report 32209 |
| 2010 | N | | | | |
| VEIN | | Assay/analysis Chip | Silver | 350 g/t | sample LC-05 |
| | | | Lead | 11.1 % | Assessment Report 32209 |
| 2010 | N | | | | |
| SAMPLE | | Assay/analysis Grab | Silver | 44.7 g/t | grab sample 86110 |
| | | | Lead | 1.27 % | Turna, R. (2009-10-05): Technical Report on the Black Bear Property). |
| 2008 | N | | | | |
| SAMPLE | | Assay/analysis Rock | Lead | 53.72 % | two samples (18-07-98-66 and 19-07-98-69) from the Trump occurrence Assessment Report 25904 |
| | | | Silver | 1938 g/t | |
| | | | Gold | 0.8 g/t | |
| | | | | | |
| 1998 | N | | | | |
| VEIN | | Assay/analysis Grab | Lead | 2.495 % | Sample 4-7131 |
| | | | Silver | 458.4 g/t | Assessment Report 13285 |
| 1984 | N | | | | |