

|                                 |                  |                         |
|---------------------------------|------------------|-------------------------|
| <b>MINFILE Number:</b> 093E 041 | <b>Name:</b> FAB | <b>Status:</b> Prospect |
|---------------------------------|------------------|-------------------------|

| Ore Zone/<br>Year/Report On | Tonnage/<br>Category | Commodity | Grade    | Reference/<br>Comments  |
|-----------------------------|----------------------|-----------|----------|---|
| SAMPLE                      |                      | Zinc      | 1.0 %    | chip samples (147525 and 147526) yielded 0.714 and 0.201 per cent copper, greater than 1.0 per cent zinc each and greater than 100 grams per tonne silver each over 1.0 metre, respectively<br>Deveaux, P.J. (2011-05-06): Coles Creek Exploration Update, 2010 |
|                             | Assay/analysis       | Silver    | 100 g/t  |   |
| 2010                        | Chip                 | Copper    | 0.714 %  |   |
|                             |                      |           |          |   |
| DRILLHOLE                   |                      | Silver    | 13.4 g/t | From a 0.91 metre drill interval.<br>Assessment Report 17228.   |
|                             | Assay/analysis       | Gold      | 0.2 g/t  |   |
| 1987                        | Drill Core           | Zinc      | 0.87 %   |   |
|                             |                      | Lead      | 0.49 %   |   |