MINFILE Number: 093F 017 **Name:** EXO **Status:** Prospect

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 2014	N	Assay/analysis Chip	Zinc Copper Tungsten Silver	1.25 % 0.16 % 0.12 % 2.6 g/t	A 1.5 metre chip sample from the Exo road quarry. Value for tungsten is WO3. Assessment Report 35268.
SAMPLE 2008	N	Assay/analysis Rock	Copper Tungsten Molybdenum Zinc Silver	1.050 % 0.303 % 0.022 % 0.186 % 16 g/t	Ray, G.E. (2008-06-30): The Geology and Mineralization at the CHES Cu-Mo-W Property
STOCKWORK 1989	N	Assay/analysis Grab	Silver Copper Molybdenum Tungsten	14.4000 g/t 0.6200 % 0.0500 % 0.0400 %	Over 350 metre width in logging road cut. George Cross Newsletter Jan.16, 1989.
SKARN 1985	N	Assay/analysis Grab	Copper Tungsten	0.4400 % 0.5600 %	Commodity is WO3. Sample over 2 metres. Skarn mineralization. Assessment Report 15129.