

<b>MINFILE Number:</b>	093F 029	<b>Name:</b>	HOLY CROSS	<b>Status:</b>	Showing
------------------------	----------	--------------	------------	----------------	---------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
2017	N	Assay/analysis Rock	Gold	0.12 g/t	Sampling was completed approximately 1 kilometre north of the Holy Cross occurrence. Highlight assays included boulder sample D005132, which graded 15.5 grams per tonne silver, and hematite outcrop sample D005123, which graded 0.12 grams per tonne gold Assessment Report 37424
			Silver	15.5 g/t	
2006	N	Assay/analysis Rock	Gold	2.91 g/t	from trench TR06-05 Morton, J.W., Goodall, G. (2007-05-22): Summary Report on the Holy Cross Property
			Silver	36.5 g/t	
2001	N	Assay/analysis Grab	Gold	24.02 g/t	Trench sample (RR19) of vitrified rhyolite with disseminated pyrite. Assessment Report 26946.
			Silver	20.8 g/t	
1996	N	Assay/analysis Grab	Gold	1.46 g/t	Assessment Report 24732.
1996	N	Assay/analysis Grab	Gold	0.416 g/t	Assessment Report 24732.
1995	N	Assay/analysis Rock	Gold	1.798 g/t	Average of four samples (54048 to 54081) from trench 1, over 4.0 metres. Assessment Report 24228.
1989	N	Assay/analysis Trench	Gold	1 g/t	Over 8.5 metres from trench 1. Assessment Report 19627.
1988	N	Assay/analysis Chip	Silver	4.3000 g/t	Average assays from 8.5 metre section in Trench 1. Assessment Report 17807.
			Gold	0.5100 g/t	