

<b>MINFILE Number:</b> 093F 061	<b>Name:</b> LOON	<b>Status:</b> Prospect
---------------------------------	-------------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SOUTHWEST 2011 N	Assay/analysis Grab	Gold	0.326 g/t	A grab sample (52327) of rhyolite, located on a hill approximately 1.5 kilometres west- south west of the Loon occurrence Assessment Report 32523
FLOAT 1995 N	Assay/analysis Grab	Gold Silver	2.94 g/t 29.4 g/t	a float boulder from trench TR95-05 Assessment Report 24229
TRENCH 1995 N	Assay/analysis Chip	Gold	0.230 g/t	over 2.0 metres in trench TR95-04 Assessment Report 24229
DRILLHOLE 1994 N	Assay/analysis Drill Core	Silver Gold	29.7000 g/t 4.2500 g/t	From DDH94-4 across 2.35 metres. Explore BC Application 1995-96.
TRENCH 1993 N	Assay/analysis Grab	Gold Silver	1.52 g/t 9.3 g/t	A grab sample (Loon Pyrite) from trench 88-4 Assessment Report 22977
TRENCH 1993 N	Assay/analysis Chip	Silver Gold	6.7 g/t 0.56 g/t	a 2.3 metre chip sample from trench 88-4 Assessment Report 22977
TRENCH 1989 N	Assay/analysis Channel	Gold Silver	0.20 g/t 4.5 g/t	. A 2-metre channel sample (00215) from trench 89-9 Assessment Report 20123
SAMPLE 1988 N	Assay/analysis Grab	Gold Silver	5.32 g/t 109.2 g/t	while a grab sample (24902) of brecciated and silicified rhyolite, taken a short distance south of trench 4 Assessment report 18637
TRENCH 1988 N	Assay/analysis Chip	Gold Silver	1.36 g/t 13.2 g/t	Chip samples from trench 4 yielded an average of 1.36 grams per tonne gold and 13.2 grams per tonne silver over 4.0 metres Assessment report 18637