

| | | |
|---------------------------------|-------------------|-------------------------|
| MINFILE Number: 093F 061 | Name: LOON | Status: Prospect |
|---------------------------------|-------------------|-------------------------|

| Ore Zone/ Year/Report On | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|-----------------------------|------------------------------|----------------|---------------------------|---|
| SOUTHWEST 2011 N | Assay/analysis Grab | Gold | 0.326 g/t | A grab sample (52327) of rhyolite, located on a hill approximately 1.5 kilometres west- south west of the Loon occurrence Assessment Report 32523 |
| FLOAT 1995 N | Assay/analysis Grab | Gold Silver | 2.94 g/t 29.4 g/t | a float boulder from trench TR95-05 Assessment Report 24229 |
| TRENCH 1995 N | Assay/analysis Chip | Gold | 0.230 g/t | over 2.0 metres in trench TR95-04 Assessment Report 24229 |
| DRILLHOLE 1994 N | Assay/analysis Drill Core | Silver Gold | 29.7000 g/t 4.2500 g/t | From DDH94-4 across 2.35 metres. Explore BC Application 1995-96. |
| TRENCH 1993 N | Assay/analysis Grab | Gold Silver | 1.52 g/t 9.3 g/t | A grab sample (Loon Pyrite) from trench 88-4 Assessment Report 22977 |
| TRENCH 1993 N | Assay/analysis Chip | Silver Gold | 6.7 g/t 0.56 g/t | a 2.3 metre chip sample from trench 88-4 Assessment Report 22977 |
| TRENCH 1989 N | Assay/analysis Channel | Gold Silver | 0.20 g/t 4.5 g/t | . A 2-metre channel sample (00215) from trench 89-9 Assessment Report 20123 |
| SAMPLE 1988 N | Assay/analysis Grab | Gold Silver | 5.32 g/t 109.2 g/t | while a grab sample (24902) of brecciated and silicified rhyolite, taken a short distance south of trench 4 Assessment report 18637 |
| TRENCH 1988 N | Assay/analysis Chip | Gold Silver | 1.36 g/t 13.2 g/t | Chip samples from trench 4 yielded an average of 1.36 grams per tonne gold and 13.2 grams per tonne silver over 4.0 metres Assessment report 18637 |