

<b>MINFILE Number:</b>	093F 077	<b>Name:</b>	BARB	<b>Status:</b>	Showing
------------------------	----------	--------------	------	----------------	---------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE		Assay/analysis Chip	Gold	0.42 g/t	A 0.3 metre chip sample (AGR-04) from a siliceous rhyolite cut by a weak quartz-pyrite stockwork Assessment Report 35887
2015	N		Molybdenum	0.051 %	
SAMPLE		Assay/analysis Grab	Gold	0.23 g/t	Sample IN004 returned 0.23 gram per tonne gold, 1.4 grams per tonne silver and 0.02476 per cent molybdenum. Sample IN004, Assessment Report 32951
2011	N		Silver	1.4 g/t	
		Molybdenum	0.02476 %		
DRILLHOLE		Assay/analysis Drill Core	Gold	2.15 g/t	A rotary drill hole (BRH-1) on the Barb zone over 1.52 metres Assessment Report 18189
1987	N				
TRENCHES		Assay/analysis Rock	Gold	1.235 g/t	three samples (4102, 4107 and Y4209) from hand trenches on the Barb zone yielded 0.565, 0.600 and 1.235 grams per tonne gold, 7.8, 6.7 and 8.0 grams per tonne silver with 0.100, 0.097 and 0.045 per cent molybdenum, respectively Assessment Report 16593
1987	N		Silver	8 g/t	
		Molybdenum	0.100 %		