

MINFILE Number:	093F 103	Name:	LIESEGANG	Status:	Showing
------------------------	----------	--------------	-----------	----------------	---------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
FLOAT			Copper	2.811 %	A grab sample from the boulder yielded 2.811 per cent Cu and 7.047 grams per tonne Ag (Geoscience BC Report 2016-1). Geoscience BC Report 2016-1
2017	N	Assay/analysis Grab	Silver	7.047 g/t	
SAMPLE			Copper	2.79 %	rock sample L017056 Assessment Report 36886
2017	N	Assay/analysis Rock	Silver	9.0 g/t	
FLOAT			Copper	3.008 %	Two float samples (2575012 and 2575013) of quartz-epidote+/-calcite veined basalt with native copper from the Liesegang occurrence yielded 2.747 and 3.008 per cent copper with 7.2 and 8.6 grams per tonne silver, respectively Assessment report 36473
2016	N	Assay/analysis Grab	Silver	8.6 g/t	