

MINFILE Number: 093F 108	Name: GEOFF	Status: Showing
---------------------------------	--------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
MAIN 2012	Assay/analysis Chip	Silver Copper	24.2 g/t 0.514 %	Twenty-two chip samples were collected from the trench over a distance of 25 metres yielding values of up to 24.2 grams per tonne silver and 0.514 per cent copper from a select composite sample of the best mineralization. Assessment Report 33483
TRENCH 1998	Assay/analysis Chip	Silver Copper Lead Zinc	4.7 g/t 0.068 % 0.181 % 0.064 %	Sampling of a trench averaged 4.7 grams per tonne silver, 0.068 per cent copper, 0.181 per cent lead and 0.064 per cent zinc over 29.5 metres with individual samples yielding up to 33.2 grams per tonne silver, 0.36 per cent copper, 1.36 per cent lead and 0.21 per cent zinc over 1.0 metre. Assessment Report 25810
SAMPLE 1996	Assay/analysis Grab	Gold Silver	0.125 g/t 40.2 g/t	A grab sample (56200) of siliceous rhyolite breccia. Assessment Report 24710