

MINFILE Number: 093J 014	Name: WICHEEDA	Status: Developed Prospect
---------------------------------	-----------------------	-----------------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments	
MAIN 2025	23,570 Indicated	kt	Rare Earths Neodymium Terbium Dysprosium Praseodymium	2.11 % 0.203 % 0.00085 % 0.00279 % 0.06977 %	"Rare Earths" = Total Rare Earth Oxide (TREO). Resources are inclusive of reserves. Reid, D. (2025-04-04): NI 43-101 Technical Report - Wicheeda Rare Earths Project PFS
MAIN 2025	5,690 Inferred	kt	Rare Earths Neodymium Terbium Dysprosium Praseodymium	1.40 % 0.1447 % 0.000765 % 0.00287 % 0.04817 %	"Rare Earths" = Total Rare Earth Oxide (TREO) Reid, D. (2025-04-04): NI 43-101 Technical Report - Wicheeda Rare Earths Project PFS
MAIN 2025	5,720 Measured	kt	Rare Earths Neodymium Terbium Dysprosium Praseodymium	2.90 % 0.264 % 0.00102 % 0.00305 % 0.09336 %	"Rare Earths" = Total Rare Earth Oxide (TREO). Resources are inclusive of reserves. Reid, D. (2025-04-04): NI 43-101 Technical Report - Wicheeda Rare Earths Project PFS
MAIN 2025	20,730 Probable	kt	Praseodymium Neodymium Terbium Dysprosium Rare Earths	0.07333 % 0.21194 % 0.00085 % 0.00279 % 2.23 %	"Rare Earths" = Total Rare Earth Oxide (TREO) Reid, D. (2025-04-04): NI 43-101 Technical Report - Wicheeda Rare Earths Project PFS
MAIN 2025	5,610 Proven	t	Rare Earths Praseodymium Neodymium Terbium Dysprosium	2.89 % 0.09312 % 0.26321 % 0.00102 % 0.00305 %	"Rare Earths" = Total Rare Earth Oxide (TREO) Reid, D. (2025-04-04): NI 43-101 Technical Report - Wicheeda Rare Earths Project PFS
MAIN 2020	4,890 Indicated	kt	Cerium Lanthanum Praseodymium Niobium Neodymium Samarium	1.26 % 0.94 % 0.11 % 0.02 % 0.26 % 0.02 %	Resulting in a total of 3.02 per cent LREE. Using a 1.5 per cent total metal cut-off grade. Defense Metals Corp. (2020-06-27): Technical Report on the Wicheeda Property, British Columbia, Canada.
MAIN 2020	12,100 Inferred	kt	Cerium Lanthanum Neodymium Praseodymium Samarium Niobium	1.20 % 0.89 % 0.27 % 0.10 % 0.02 % 0.04 %	Resulting in a total of 2.9 per cent LREE. Using a 1.5 per cent total metal cut-off grade. Defense Metals Corp. (2020-06-27): Technical Report on the Wicheeda Property, British Columbia, Canada.
MAIN 2018	11,370 Inferred	kt	Rare Earths Cerium Lanthanum Niobium Neodymium Samarium	1.96 % 1.14 % 0.53 % 0.04 % 0.23 % 0.01 %	1.96 per cent LREE. Calculated at 1.0 LREE per cent cut-off. News Release Defence Metals Corp. January 8, 2019.