

MINFILE Number: 093J 014	Name: WICHEEDA	Status: Developed Prospect
---------------------------------	-----------------------	-----------------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
MAIN 2025	23,570 Indicated	kt	Rare Earths 2.11 % Neodymium 0.203 % Terbium 0.00085 % Dysprosium 0.00279 % Praseodymium 0.06977 %	"Rare Earths" = Total Rare Earth Oxide (TREO). Resources are inclusive of reserves. Reid, D. (2025-04-04): NI 43-101 Technical Report - Wicheeda Rare Earths Project PFS
MAIN 2025	5,690 Inferred	kt	Rare Earths 1.40 % Neodymium 0.1447 % Terbium 0.000765 % Dysprosium 0.00287 % Praseodymium 0.04817 %	"Rare Earths" = Total Rare Earth Oxide (TREO) Reid, D. (2025-04-04): NI 43-101 Technical Report - Wicheeda Rare Earths Project PFS
MAIN 2025	5,720 Measured	kt	Rare Earths 2.90 % Neodymium 0.264 % Terbium 0.00102 % Dysprosium 0.00305 % Praseodymium 0.09336 %	"Rare Earths" = Total Rare Earth Oxide (TREO). Resources are inclusive of reserves. Reid, D. (2025-04-04): NI 43-101 Technical Report - Wicheeda Rare Earths Project PFS
MAIN 2025	20,730 Probable	kt	Praseodymium 0.07333 % Neodymium 0.21194 % Terbium 0.00085 % Dysprosium 0.00279 % Rare Earths 2.23 %	"Rare Earths" = Total Rare Earth Oxide (TREO) Reid, D. (2025-04-04): NI 43-101 Technical Report - Wicheeda Rare Earths Project PFS
MAIN 2025	5,610 Proven	t	Rare Earths 2.89 % Praseodymium 0.09312 % Neodymium 0.26321 % Terbium 0.00102 % Dysprosium 0.00305 %	"Rare Earths" = Total Rare Earth Oxide (TREO) Reid, D. (2025-04-04): NI 43-101 Technical Report - Wicheeda Rare Earths Project PFS
MAIN 2020	4,890 Indicated	kt	Cerium 1.26 % Lanthanum 0.94 % Praseodymium 0.11 % Niobium 0.02 % Neodymium 0.26 % Samarium 0.02 %	Resulting in a total of 3.02 per cent LREE. Using a 1.5 per cent total metal cut-off grade. Defense Metals Corp. (2020-06-27): Technical Report on the Wicheeda Property, British Columbia, Canada.
MAIN 2020	12,100 Inferred	kt	Cerium 1.20 % Lanthanum 0.89 % Neodymium 0.27 % Praseodymium 0.10 % Samarium 0.02 % Niobium 0.04 %	Resulting in a total of 2.9 per cent LREE. Using a 1.5 per cent total metal cut-off grade. Defense Metals Corp. (2020-06-27): Technical Report on the Wicheeda Property, British Columbia, Canada.
MAIN 2018	11,370 Inferred	kt	Rare Earths 1.96 % Cerium 1.14 % Lanthanum 0.53 % Niobium 0.04 % Neodymium 0.23 % Samarium 0.01 %	1.96 per cent LREE. Calculated at 1.0 LREE per cent cut-off. News Release Defence Metals Corp. January 8, 2019.