MINFILE Number: 093J 025 **Name:** GISCOME **Status:** Producer

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
TOTAL			Limestone	98.0000 %	Quarried limestone averages at least 98 per cent CaCO3. G. Klein, personal communication, 1991.
1990	N	Assay/analysis Bulk Sample			