

| | | | | | |
|------------------------|----------|--------------|------------|----------------|---------------|
| MINFILE Number: | 093K 026 | Name: | SILVER FOX | Status: | Past Producer |
|------------------------|----------|--------------|------------|----------------|---------------|

| Ore Zone/ Year/Report On | | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|-----------------------------|---|------------------------------|-----------|---------------|---|
| SAMPLE | | Assay/analysis Rock | Gold | 15.5 g/t | A sample (no. 1) of mineralized quartz |
| 1984 | N | | Silver | 20.6 g/t | Assessment Report 13201 |
| SAMPLE | | Assay/analysis Rock | Gold | 6.5 g/t | Assessment Report 10647 |
| 1982 | N | | Silver | 6300 g/t | |
| | | | Lead | 6.8 % | |
| | | | Zinc | 9.8 % | |
| DUMP | | Assay/analysis Grab | Gold | 1.4 g/t | . A sample (71152) from the dump of the Silver Fox shaft Property File - 800790 |
| 1967 | N | | Silver | 527 g/t | |
| | | | Copper | 0.94 % | |
| DRILLHOLE | | Assay/analysis Drill Core | Silver | 2646.9000 g/t | Drill intersection over 2.1 metres. Minister of Mines Annual Report 1928, page 177. |
| 1928 | N | | Gold | 1.0300 g/t | |
| | | | Copper | 1.9000 % | |
| | | | Zinc | 5.1000 % | |
| SHAFT | | Assay/analysis Chip | Gold | 5.5 g/t | Sampling of the shaft yielded assays including 12.3 grams per tonne gold, 2320 grams per tonne silver, 1.2 per cent copper, 17.5 per cent lead and 13.8 per cent zinc over 0.48 metre at a depth of 36.0 metres and 5.5 grams per tonne gold, 8800 grams per tonne silver, 11.6 per cent lead and 12.5 per cent zinc over 0.38 metre at a depth of 42.0 metres Assessment Report 11584 |
| 1928 | N | | Silver | 8800 g/t | |
| | | | Lead | 11.6 % | |
| | | | Zinc | 12.5 % | |
| DRILLHOLE | | Assay/analysis Drill Core | Gold | 1.03 g/t | a drill hole was completed on the ‘High-grade’ vein and at depths of 64.8 and 90.9 metres the drill intersection two 2.1 metre sections yielding 1.03 and 1.03 grams per tonne gold, 430.9 and 2646.9 grams per tonne silver, trace and 1.9 per cent copper, 7.8 and trace per cent lead with 2.4 and 5.1 per cent zinc, respectively Annual Report 1928, p.177 |
| 1927 | N | | Silver | 2646.9 g/t | |
| | | | Copper | 1.9 % | |
| | | | Zinc | 5.1 % | |
| DUMP | | Assay/analysis Grab | Silver | 123.5 g/t | , a sample of adit dump material Property File Rimfire Windflower Mining Ltd., 1985 |
| 1925 | N | | Copper | 1 % | |
| | | | Lead | 3 % | |
| | | | Zinc | 27 % | |