

|                                 |                         |                              |
|---------------------------------|-------------------------|------------------------------|
| <b>MINFILE Number:</b> 093K 026 | <b>Name:</b> SILVER FOX | <b>Status:</b> Past Producer |
|---------------------------------|-------------------------|------------------------------|

| Ore Zone/<br>Year/Report On | Tonnage/<br>Category         | Commodity | Grade         | Reference/<br>Comments  |
|-----------------------------|------------------------------|-----------|---------------|---|
| SAMPLE                      |                              | Gold      | 15.5 g/t      | A sample (no. 1) of mineralized quartz<br>Assessment Report 13201   |
| 1984                        | Assay/analysis<br>Rock       | Silver    | 20.6 g/t      |   |
| SAMPLE                      |                              | Gold      | 6.5 g/t       | Assessment Report 10647   |
| 1982                        | Assay/analysis<br>Rock       | Silver    | 6300 g/t      |   |
|                             |                              | Lead      | 6.8 %         |   |
|                             |                              | Zinc      | 9.8 %         |   |
| DUMP                        |                              | Gold      | 1.4 g/t       | . A sample (71152) from the dump of the Silver Fox<br>shaft<br>Property File - 800790   |
| 1967                        | Assay/analysis<br>Grab       | Silver    | 527 g/t       |   |
|                             |                              | Copper    | 0.94 %        |   |
| DRILLHOLE                   |                              | Silver    | 2646.9000 g/t | Drill intersection over 2.1 metres.<br>Minister of Mines Annual Report 1928, page 177.  |
| 1928                        | Assay/analysis<br>Drill Core | Gold      | 1.0300 g/t    |   |
|                             |                              | Copper    | 1.9000 %      |   |
|                             |                              | Zinc      | 5.1000 %      |   |
| SHAFT                       |                              | Gold      | 5.5 g/t       | Sampling of the shaft yielded assays including 12.3<br>grams per tonne gold, 2320 grams per tonne silver, 1.2<br>per cent copper, 17.5 per cent lead and 13.8 per cent<br>zinc over 0.48 metre at a depth of 36.0 metres and 5.5<br>grams per tonne gold, 8800 grams per tonne silver, 11.6<br>per cent lead and 12.5 per cent zinc over 0.38 metre at a<br>depth of 42.0 metres<br>Assessment Report 11584 |
| 1928                        | Assay/analysis<br>Chip       | Silver    | 8800 g/t      |   |
|                             |                              | Lead      | 11.6 %        |   |
|                             |                              | Zinc      | 12.5 %        |   |
| DRILLHOLE                   |                              | Gold      | 1.03 g/t      |   |
| 1927                        | Assay/analysis<br>Drill Core | Silver    | 2646.9 g/t    | a drill hole was completed on the 'High-grade' vein and<br>at depths of 64.8 and 90.9 metres the drill intersection<br>two 2.1 metre sections yielding 1.03 and 1.03 grams per<br>tonne gold, 430.9 and 2646.9 grams per tonne silver,<br>trace and 1.9 per cent copper, 7.8 and trace per cent<br>lead with 2.4 and 5.1 per cent zinc, respectively<br>Annual Report 1928, p.177                           |
|                             |                              | Copper    | 1.9 %         |   |
|                             |                              | Zinc      | 5.1 %         |   |
| DUMP                        |                              | Silver    | 123.5 g/t     |   |
| 1925                        | Assay/analysis<br>Grab       | Copper    | 1 %           | , a sample of adit dump material<br>Property File Rimfire Windflower Mining Ltd., 1985  |
|                             |                              | Lead      | 3 %           |   |
|                             |                              | Zinc      | 27 %          |   |