MINFILE Number: 093K 041 **Name:** VAN DECAR CREEK **Status:** Prospect

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 2010 N	Assay/analysis Rock	Nickel	0.206 %	Surface rock samples yielded from 0.134 to 0.268 per cent nickel and averaged 0.206 per cent nickel. Verley, C.G. (2011-02-14): Report on the Decar Nickel Property (Pursuant to National Instrument 43-101 of the Canadian Securities Administrators) Trembleur Lake Area
SOUTH 1998 N	Assay/analysis Rock	Nickel	0.210 %	Five samples (Road-1 through -5) taken from near the east side of the east arm of Van Decar Creek, approximately 1.4 kilometres south-southwest of the Van Decar Creek occurrence, of dunite, serpentinite and harzburgite with disseminated awaruite yielded from 0.156 to 0.210 per cent nickel. Assessment Report 25727
TRENCH 1979 N	Assay/analysis Rock	Chromium Nickel	38.9 % 0.190 %	Four samples from a hand trench on the main zone yielded values from 17.7 to 38.9 per cent chromium, 0.096 to 0.190 per cent nickel and 0.012 to 0.018 per cent cobalt. Assessment Report 8135