MINFILE Number: 093K 091 **Name:** FREE GOLD ZONE **Status:** Showing

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 1985 N	Assay/analysis Grab	Gold Copper Silver	3.33 g/t 2.70 % 37.4 g/t	three select grab samples (39251, 39252 and 055052) of syenodiorite and/or syenite to monzonite with clots of chalcopyrite from the Freegold zone yielded from 2.20 to 3.33 grams per tonne gold, 6.2 to 37.4 grams per tonne silver and 1.00 to 2.70 per cent copper Property File - 673703
SAMPLE 1984 N	Assay/analysis Grab	Gold	54.79 g/t	sample with visible gold from the Free Gold zone Assessment Report 25839