

| | | |
|---------------------------------|-----------------------------|------------------------|
| MINFILE Number: 093K 091 | Name: FREE GOLD ZONE | Status: Showing |
|---------------------------------|-----------------------------|------------------------|

| Ore Zone/ Year/Report On | Tonnage/ Category | Commodity | Grade | Reference/ Comments |
|-----------------------------|-----------------------------|--------------------------|--------------------------------|---|
| SAMPLE 1985 | N Assay/analysis Grab | Gold Copper Silver | 3.33 g/t 2.70 % 37.4 g/t | three select grab samples (39251, 39252 and 055052) of syenodiorite and/or syenite to monzonite with clots of chalcopyrite from the Freegold zone yielded from 2.20 to 3.33 grams per tonne gold, 6.2 to 37.4 grams per tonne silver and 1.00 to 2.70 per cent copper Property File - 673703 |
| SAMPLE 1984 | N Assay/analysis Grab | Gold | 54.79 g/t | sample with visible gold from the Free Gold zone Assessment Report 25839 |