MINFILE Number: 093K 116 **Name:** BAPTISTE (DECAR) **Status:** Developed Prospect

Ore Zone/ Year/Report On		Tonnage/ Category		Commodity	Grade	Reference/ Comments
TOTAL		1,995,873	kt	Nickel	0.122 %	Using a 0.06 nickel cut-off grade.
		Indicated				Grandillo, A., Voordouw, R. (2021-03-17): NI 43-101
2020	Y					Technical Report, Preliminary Economic Assessment, Baptiste Nickel Project, British Columbia, Canada
TOTAL		592,890	kt	Nickel	0.114 %	Using a 0.06 nickel cut-off grade.
		Inferred				Grandillo, A., Voordouw, R. (2021-03-17): NI 43-101
2020	Y					Technical Report, Preliminary Economic Assessment, Baptiste Nickel Project, British Columbia, Canada
PIT		1,842,645	kt	Nickel	0.123 %	A pit-constrained updated mineral resource estimate.
		Indicated				Voordouw, R.J., Simpson, R.G. (2018-02-26): 2018
2018	Y					Technical (N.I. 43-101) Report on the Decar Nickel-Iron Alloy Property
PIT		390,788	kt	Nickel	0.115 %	A pit-constrained updated mineral resource estimate.
		Inferred				Voordouw, R.J., Simpson, R.G. (2018-02-26): 2018
2018	Y					Technical (N.I. 43-101) Report on the Decar Nickel-Iron Alloy Property
TOTAL		1,160,000	kt	Nickel	0.124 %	
		Indicated				Information Circular 2018-1, page 47.
2013	Y					
TOTAL		870,000	kt	Nickel	0.125 %	
		Inferred				Information Circular 2018-1, page 47.
2013	Y					