

<b>MINFILE Number:</b> 093M 064	<b>Name:</b> BRIAN BORU (L. 607)	<b>Status:</b> Prospect
---------------------------------	----------------------------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE  2008	Assay/analysis Grab	Silver Copper Zinc Gold Cobalt	152.0 g/t 0.50 % 22.27 % 1.11 g/t 0.019 %	The most notable samples collected were sample 23201, which was a massive sulphide boulder dominantly comprised of sphalerite and pyrrhotite, and sample 23176, which was highly limonitic, but otherwise similarly massive sphalerite and pyrrhotite. Samples 23201 and 23176 assayed 0.10 and 1.11 grams per tonne gold, 152.0 and 66.0 grams per tonne silver, 0.50 and 0.13 per cent copper, 14.26 and 22.27 per cent zinc with 0.013 and 0.019 per cent cobalt, respectively Assessment Report 30431
SAMPLE  1954	Assay/analysis Channel	Silver Lead Zinc	220.5000 g/t 1.8400 % 11.2700 %	A 15-centimetre channel sample. Geological Survey of Canada Memoir 223 (1954), page 35.