

<b>MINFILE Number:</b>	093M 074	<b>Name:</b>	GOLDEN WONDER (L. 3322)	<b>Status:</b>	Showing
------------------------	----------	--------------	-------------------------	----------------	---------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
2019	N	Assay/analysis Rock	Gold	1.91 g/t	Reeder, J.J. (2021-03-08): Technical Report on the Golden Wonder Property, South of New Hazelton, British Columbia, Canada
			Copper	0.41 %	
2017	Y	Assay/analysis Chip	Gold	20 g/t	A chip sample (128288) of oxidized breccia with massive arsenopyrite veins. Reeder, J.J. (2019-05-21): Technical Report on the Golden Wonder Property
			Silver	16.4 g/t	
2017	N	Assay/analysis Chip	Gold	18.7 g/t	A chip sample (128278) of oxidized mudstone with a 1.5-metre wide breccia zone hosting massive sulphides and quartz. Reeder, J.J. (2019-05-21): Technical Report on the Golden Wonder Property
			Silver	100 g/t	
			Cobalt	0.653 %	
			Copper	0.97 %	
2011	N	Assay/analysis Chip	Gold	1.29 g/t	A 0.2-metre chip sample from a zone located approximately 450 metres to the south west of the main pit. Reeder, J.J. (2019-05-21): Technical Report on the Golden Wonder Property
			Silver	6.7 g/t	
			Copper	0.234 %	
2011	N	Assay/analysis Rock	Gold	21.9 g/t	A rock sample from the main pit area. Reeder, J.J. (2019-05-21): Technical Report on the Golden Wonder Property
			Silver	104 g/t	
			Copper	3.1 %	
			Cobalt	1.21 %	
2007	N	Assay/analysis Chip	Copper	1.02 %	Chip sample (RD07-018) from a gravel pit located approximately 500 metres to the west. Burgoyne, A.A., Kikauka, A. (2007-12-18): Technical Report on the Rocher Deboule Property
			Gold	5.42 g/t	
			Cobalt	0.116 %	
2007	N	Assay/analysis Chip	Gold	4.93 g/t	Chip sample (76051) over 0.6 metre. Burgoyne, A.A., Kikauka, A. (2007-12-18): Technical Report on the Rocher Deboule Property
			Silver	54.2 g/t	
			Copper	3.3 %	
			Cobalt	0.198 %	
1980	N	Assay/analysis Chip	Silver	21.6000 g/t	A 60-centimetre sample. Assessment Report 8521.
			Gold	5.5500 g/t	
			Cobalt	0.1300 %	
			Copper	1.2100 %	