

|                        |          |              |             |                |          |
|------------------------|----------|--------------|-------------|----------------|----------|
| <b>MINFILE Number:</b> | 093M 081 | <b>Name:</b> | GOLDEN GIRL | <b>Status:</b> | Prospect |
|------------------------|----------|--------------|-------------|----------------|----------|

| Ore Zone/<br>Year/Report On |   | Tonnage/<br>Category   | Commodity | Grade         | Reference/<br>Comments  |
|-----------------------------|---|------------------------|-----------|---------------|---|
| SAMPLE<br><br>2018          | N | Assay/analysis<br>Rock | Silver    | 282 g/t       | Two rock samples (GL-18-1 and GL-18-2), collected in 2018, assayed 160 and 282 grams per tonne silver, 2.64 and 1.80 per cent lead with 1.90 and 6.13 per cent zinc, respectively<br>Butler, S.P. (2019-09-17): Technical Report on the Golden Girl propert |
|                             |   |                        | Lead      | 1.80 %        |   |
|                             |   |                        | Zinc      | 6.13 %        |   |
|                             |   |                        |           |               |   |
| SAMPLE<br><br>1988          | N | Assay/analysis<br>Chip | Silver    | 3182.1000 g/t | A 20-centimetre sample width.<br>Assessment Report 17291.   |
|                             |   |                        | Gold      | 1.0000 g/t    |   |