

MINFILE Number:	093M 151	Name:	FIREWEED	Status:	Developed Prospect
------------------------	----------	--------------	----------	----------------	--------------------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
2011	N	Assay/analysis Drill Core	Silver	444.4 g/t	Over 15.1 metres in drillhole FW 11-4. Press Release - Shamrock Enterprises Inc., April 18, 2012.
			Lead	1.3 %	
			Zinc	2.4 %	
2010	N	Assay/analysis Drill Core	Silver	64.6 g/t	Over 28.79 metres in drillhole FW 10-1. Assessment Report 32156.
			Lead	2.27 %	
			Zinc	4.64 %	
			Gold	1.05 g/t	
1989	Y	584,500 t Indicated	Silver	341.7700 g/t	Cutoff grade is 171.4 grams per tonne silver at an average width of 4.75 metres. George Cross News Letter No.66, 1989.
			Lead	1.3400 %	
			Zinc	2.2200 %	