

MINFILE Number: 093M 162	Name: COPPER 1-4	Status: Showing
---------------------------------	-------------------------	------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
FLOAT 2017	N Assay/analysis Grab	Lead Zinc Copper Silver	20 % 21.4 % 0.585 % 1295 g/t	two samples (1043627 and 1043628) of broken bedrock float quartz with galena, sphalerite and chalcopyrite assayed greater than 20 per cent lead each, 12 and 21.4 per cent zinc, 0.585 and 0.131 per cent copper with 1295 and 939 grams per tonne silver, respectively Assessment Report 37532
SAMPLE 2017	N Assay/analysis Grab	Zinc	0.594 %	A grab sample (1043624) of broken bedrock comprising an oxidized fine-grained sediment with galena and chalcopyrite(?) Assessment Report 37532
SAMPLE 1987	N Assay/analysis Grab	Silver Lead Zinc	713.7000 g/t 23.0000 % 13.5000 %	Highest assay from samples. Sample taken across 10 centimetres of vein and 5 centimetres of wallrock. Less than 0.1 grams per tonne Au. Property File - Gold Canyon Resources Inc., Prospectus, 1987.