

<b>MINFILE Number:</b>	093M 162	<b>Name:</b>	COPPER 1-4	<b>Status:</b>	Showing
------------------------	----------	--------------	------------	----------------	---------

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
FLOAT			Lead	20 %	two samples (1043627 and 1043628) of broken bedrock float quartz with galena, sphalerite and chalcopyrite assayed greater than 20 per cent lead each, 12 and 21.4 per cent zinc, 0.585 and 0.131 per cent copper with 1295 and 939 grams per tonne silver, respectively Assessment Report 37532
		Assay/analysis	Zinc	21.4 %	
2017	N	Grab	Copper	0.585 %	
			Silver	1295 g/t	
SAMPLE			Zinc	0.594 %	A grab sample (1043624) of broken bedrock comprising an oxidized fine-grained sediment with galena and chalcopyrite(?) Assessment Report 37532
2017	N	Assay/analysis Grab			
SAMPLE			Silver	713.7000 g/t	Highest assay from samples. Sample taken across 10 centimetres of vein and 5 centimetres of wallrock. Less than 0.1 grams per tonne Au. Property File - Gold Canyon Resources Inc., Prospectus, 1987.
		Assay/analysis	Lead	23.0000 %	
1987	N	Grab	Zinc	13.5000 %	