

<b>MINFILE Number:</b> 093N 067	<b>Name:</b> TAK	<b>Status:</b> Prospect
---------------------------------	------------------	-------------------------

Ore Zone/ Year/Report On	Tonnage/ Category	Commodity	Grade	Reference/ Comments
SAMPLE 1991 N	Assay/analysis Grab	Copper Silver Gold	0.741 % 3.1 g/t 0.15 g/t	grab sample P91NL049 Assessment Report 22192
SAMPLE 1991 N	Assay/analysis Chip	Gold	0.36 g/t	chip sample P91NL048 over 0.5 metre Assessment Report 22192
SAMPLE 1991 N	Assay/analysis Grab	Silver Gold Copper	40.5000 g/t 1.8000 g/t 1.5300 %	Sample (10129) is a malachite/azurite stained hybrid intrusion with 5 per cent semimassive chalcopryrite from the Goat Ridge area. Assessment Report 20838, Appendix 2.
SAMPLE 1990 N	Assay/analysis Grab	Copper Gold Silver	1.53 % 1.80 g/t 40.5 g/t	a grab sample (10129) of epidotized and malachite-azurite stained hybrid intrusive rock hosting up to 5 per cent chalcopryrite in semi-massive pods from a showing on the Goat Ridge zone Assessment Report 20838
SAMPLE 1985 N	Assay/analysis Grab	Copper Silver Gold	1.24 % 33.2 g/t 0.73 g/t	sample NS25-B Assessment Report 15652
SAMPLE 1969 N	Assay/analysis Chip	Copper	1.56 %	three chip samples (OS-1 through -3) yielded 0.84, 0.36 and 1.56 per cent copper over 3.0, 3.6 and 2.1 metres, respectively Property File - Kikuchi, T. [1969-10-03]: Preliminary Geological Report on the Omineca Show Property
HIGH-GRADE 1966 N	Assay/analysis Rock	Copper Silver Gold	4.31 % 37.7 g/t 0.69 g/t	a high-grade sample (6369), while two other samples (6367 and 6368) from the north and south ends of the mineralized zone yielded 1.11 and 2.06 per cent copper, respectively, with 10.3 grams per tonne silver and 0.69 gram per tonne gold, each Assessment Report 816