MINFILE Number: 093N 272 **Name:** TRS **Status:** Prospect

Ore Zone/ Year/Report On		Tonnage/ Category	Commodity	Grade	Reference/ Comments
FLOAT 1990	N	Assay/analysis Grab	Copper Silver Gold	2.12 % 59.4 g/t 19.43 g/t	float samples (TR-90-D35, -D36 and R3) taken down slope of the veins yielded values from 0.15 to 2.12 per cent copper, 6.1 to 59.4 grams per tonne silver and 8.29 to 19.43 grams per tonne gold Assessment Report 22372
NORTHEAST 1990	N	Assay/analysis Grab	Silver Gold	11.7 g/t 0.93 g/t	grab samples (TR-90-D5 and -D6) from outcrops of tuff and epidote altered granite with quarts veinlets and trace chalcopyrite and pyrite, located approximately 500 metres north east of the main veined zone Assessment Report 22372
OUTCROP 1990	N	Assay/analysis Rock	Gold Silver Copper	1.56 g/t 4.4 g/t 0.30 %	two grab samples (TR-90-D44 and -D45) of quartz veined outcrop Assessment Report 22372
TRENCH 1990	N	Assay/analysis Chip	Gold Silver Copper Lead	3.66 g/t 24.0 g/t 0.54 % 1.44 %	over 1.0 metre in trench TR-90-T5 Assessment Report 22372
VEIN 1987	N	Assay/analysis Channel	Gold Silver Copper	1.250 g/t 3.3 g/t 0.146 %	a 3-centimetre channel sample (TRS-9) from a chalcopyrite-bearing quartz vein in a granite porphyry Assessment Report 16759
DRILLHOLE 1987	N	Assay/analysis Drill Core	Gold Copper	1.06 g/t 0.490 %	over 1.52 metres (2.74 to 4.26 metres down-hole), including 0.490 per cent copper over 0.62 metre from a oxidized andesitic volcanic with thin quartz-calcite veinlets in hole TRS 87-1 Assessment Report 16759
DRILLHOLE 1987	N	Assay/analysis Drill Core	Lead Zinc Silver	1.62 % 2.99 % 254.4 g/t	over 1.0 metre (from 65.55 to 66.55 metres down-hole) from a silicified to quartz brecciated andesitic volcanic hosting disseminated pyrite in hole TRS 87-4 Assessment Report 16759
SAMPLE 1986	N	Assay/analysis Chip	Gold	0.350 g/t	three chip samples (TRS-103R, -118R and -124R) of the intrusive host yielded 0.102, 0.350 and 0.200 gram per tonne gold over 1.0, 1.0 and 2.5 metres, respectively, while a grab sample (TRS-5R) of the intrusive yielded 0.960 gram per tonne gold Assessment Report 15319